

## MEDIUM OIL ALKYD RESIN

## ALKYD MO-1556-WS

### FEATURES

- External / Internal Decorative Paints
- Fast Drying End good Outdoor Durability
- Good Adhesion On Surface

### DELIVERY FORM DETAILS

- good performance in industrial paints
- good gloss finishes

### Characteristics

- |  |              |
|--|--------------|
| • Oil Length                             | 46 %         |
| • Solids                                 | 55 ± 1 %     |
| • Solvent                                | White Spirit |
| • Oil Type                               | SOFA         |
| • Color Gardner                          | 4 max        |
| • Viscosity Gardner                      | >Z6          |
| • Final Viscosity (Ford cup4<br>At 27°C) | 200 ± 10 sec |
| • Acid Value (on Solids)                 | 15 max       |

### SOLUBILITY DATA

- |                      |           |
|----------------------|-----------|
| • Aliphatic Solvents | Soluble   |
| • Aromatic Solvents  | Soluble   |
| • Ketones            | Soluble   |
| • Alcohols           | Insoluble |
| • Esters             | Soluble   |

### COMPATIBILITY DATA

- |                    |            |
|--------------------|------------|
| • Medium Oil Alkyd | Compatible |
| • Long Oil Alkyd   | Compatible |
| • Rosin Maleate    | Compatible |

### DELIVERY FORM DETAILS:

- 55 % in White Spirit – Drums (185 kg / drum)

### SHELF LIFE

- Shelf life is minimum 12 months when stored under standard storage conditions

**Disclaimer** (Updated On March 2013)

#### DISCLAIMER

This information contained in the data sheet is to the best of our knowledge correct and up to date. Under well-defined conditions. Its accuracy or suitability under the actual conditions of any independent use is not guaranteed and must be determined by the user. All advice given about this product is given in good faith. Since as we have no control over conditions of substrate, manufacturer and seller cannot accept any liability in connection with the use of the product relative to coverage, performance, injury, or damage, unless we specify in writing to do so. The information in this data sheet is subject to change without prior notice and it is the user responsibility to ensure it is current. For further information and advice please contact RAR RESIN Technical Service Department.